



RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth.



1L | 1171105-001

4L | 1171105-004

20L | 1171105-020

20L | 1171105-B20

60L | 1171105-060

208L | 1171105-208

208L | 1171105-D28

Kategorie: Motorbike engine oil

Artikelnummer: 1171105

Viscosity: 20W-50

Specifications: API SL, JASO MA2

Oil type: Full synthetic

Recommendations: BMW Cruiser Motorcycles, Harley Davidson 62600005, Harley Davidson 62600031, Honda 08C35-A251L01, Honda 08C35-A251M02, Indian Motorcycles, Moto Guzzi, Suzuki V-twin Motor Oil, Triumph, Victory Motorcycles, Yamalube LUB20W50AP12, Yamalube LUB20W50AP05

Application: Motorcycle

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is a high grade, full synthetic 3-in-1 lubricant for engine, drive and crank shaft, that was specially designed for cruiser and chopper motorcycles. Thanks to its synthetic components and specifically attuned, innovative additives, it is excellently suited for the demanding engines, drives and crankshafts of cruise and chopper motorcycles.

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. reduces the friction and reliably protects the valves and the crankshaft against metal-to-metal contact. The consistent viscosity reduces load peaks at high temperatures.

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. demonstrates excellent stability and durability against thermal loads under extremely high temperatures that can occur in air-cooled V-twin engines.

Application instructions

RAVENOL Motobike V-Twin SAE 20W-50 Fullsynth. is suitable as an engine oil for all V-twin chopper and cruiser motorcycles if the specification SAE 20W-50 is required.

Characteristics

- a very stable and outstanding viscosity behaviour
- reduced friction
- outstanding viscosity temperature characteristics
- a reliable lubrication film at extremely high operating temperatures
- very good protection against wear and corrosion
- protection against foaming
- excellent deterging and dispersing properties

Technical Product Data

CHARACTERISTICS	PROPERTY	DATA	AUDIT
Colour		braun	VISUELL
tbn	mg KOH/g	7,4	ASTM D2896
Viscosity at 100 °C	mm ² /s	19,8	DIN 51562-1
Viscosity at 40 °C	mm ² /s	139,67	DIN 51562-1
Viscosity Index VI		163	DIN ISO 2909
CCS Viscosity at -15 °C	mPa*s	4473	ASTM D5293
Density at 20 °C	kg/m ³	858,0	EN ISO 12185
Flashpoint	°C	252	DIN EN ISO 2592
Pourpoint	°C	-42	DIN ISO 3016